

Product	Aluminium Coil / Sheets
Customer Name:	Intita Engineering Services Pvt Ltd.
Specification	3x 1200x 2500 mm, 3x 1200x 3000 mm.
Alloy	3003
Temper	H14
OD/weight	NA
ID	NA
Thickness Tolerance in mm	as per standards [IS 2676]
Width Tolerance in mm	as per standards [IS 2676]
Surface	MPEL finish.
Build up	-
Chemical Composition	As per IS 737-2008
Alloy - 3003.H14 - Detailed chemical composition to be given.	
	Si 0.6 Max
	Fe 0.7 Max
	Cu 0.05 - 0.2 Max
	Mn 1.0 - 1.5 Max
	Mg 0.1 Max
	Cr -
	Zn 0.1 Max
	Ti -
	Al Remainder
Mechanical properties	As per IS 737-2008
Tensile strength (Mpa)	140 MPa - 180 MPa.
Tensile strength (Mpa) Target to achieve	140 MPa.
Elongation	6%.
End Use	Aluminium formwork Panels.

Important instructions, if any -

  
 09/11/2020  
**JINDAL ALUMINIUM LIMITED**  
 (Rolling Mill Division)  
 K.T.A.D.B. Industrial Area  
 Yedahalli Village, Tumkur Road  
 Dabbaspeta, Bengaluru-562 111  
 Ph: 080-27735051-27735003

  
 #1120

