

TECHNICAL DATA SHEET

| | |
|--|--|
| TDS No. | Date : 24.12.2020 |
| 1 NAME OF CUSTOMER : | K. K. IMPEX |
| 2 PRODUCT | ALUMINIUM SHEET |
| 3 END APPLICATION | BUILDING FAÇADE |
| PRODUCT SPECIFICATIONS | |
| 4 ALLOY | AA 1100 |
| 5 TEMPER | H14 |
| 6 CHEMICAL COMPOSITION | AS PER IS 737-2008 STANDARD |
| 7 DIMENSIONS & TOLERANCE | |
| a) THICKNESS (mm) | 2.00MM THICKNESS (Tol. ± 0.040 mm) |
| b) WIDTH (mm) | 1000MM/1220 MM (Tol. ± 1.0 mm) |
| c) Length (mm) | 2440MM & OTHERS LENGTH (Tol. ± 3.0 mm for 1220 to 2440 mm, $-3/+5$ mm for 2440 to 3660 mm, $-4/+7$ mm for over 3660 mm) |
| d) Dia(mm) - FOR CIRCLE | N/A |
| 8 COIL DIAMETER | |
| a) Internal Diameter of coil (mm) | N/A |
| b) Maximum Outer Diameter of coil (mm) | N/A |
| 9 a) Coil Weight (Min./Max) | AS PER P.O. |
| b) Coil Build up | N/A |
| 10 TENSILE STRENGTH | 110 - 145 Mpa |
| 11 Elongation | Min 5% |
| 12 Resistivity | N/A |
| 13 Surface Finish | SMOOTH, FLAT & GOOD SURFACE FINISH WITHOUT ANY PIT/DENT/BLACK/WHITE SPOT & SCRATCHES |
| 14 Edges | FINE |
| 15 SPECIAL PACKING REQUIREMENTS | STANDARD HDPE + PALLET + POLYINTERLEAVING |
| 16 SPECIAL REQUIREMENT | SHEET SHOULD BE HAVING GOOD FLATNESS & BENDING QUALITY AND SUITABLE FOR BUILDING FACADE . Cross bending required. |
| For <i>K K Impex</i> | ACCEPTED |
| <i>Abhinav Jain</i> | For Jindal Aluminium Limited (Rolling Div.) |
| <i>Rajiv</i> | <i>R.N. Sahu</i> |
| Name & Designation of Customer Rep. | Name & Designation |

K K IMPEX
H3/3 DLF Phase-I
Gurgaon-122002
GSTIN. 06AAKFK7268C1Z **Partner**

JINDAL ALUMINIUM LIMITED
(Rolling Mill Division)
K.I.A.D.B. Industrial Area
Yedahalli Village, Tumkur Road
Dabbaspeta, Bengaluru-562 111
Ph: 080-27735051-27735000